

Materials

33 - Saturno Pvc (REV.00) CAT.B



33-001A
Bianco



33-003A
Bianco ghiaccio



33-016A
Nero



33-151A
Blu denim



33-280A
Scarafaggio



33-390A
Rosso



33-747A
Avorio chiaro



33-776A
Lino



33-777A
Grigio nuvola



33-783A
Camoscio



33-791A
Grigio



33-792A
Grigio scuro



33-799A
Caffè



33-800A
Kaki



33-804A
Rosso chilli



33-991A
Bianco off



33-992A
Champagne



Price List 2021



Frag 33 Saturno Pcv is smooth, with an even surface and is soft and silky to the touch. It is entirely manufactured in Italy, where total control of the production process and treatments guarantees quality and durability. An ideal material for our chairs and sofas.

Durable and easy to clean, it is resistant to wear and stretching and retains its colour with normal use. Available in a wide range of colours, it is an ideal material for a variety of furnishing projects, especially for contract use.

Composition:
PVC 69% - PES 20% - CO 10% - PU 1%
Weight: 580 +/- 10 gr/m²

Thickness: 1,00 +/- 0,10 mm
Width: 140 +/- 2 cm
Repeat: None

Tensile strenght	UNI EN ISO 1421:2000	Warp ≥ 500 N/5 cm / Weft ≥ 350 N / 5 cm
Tear strenght	UNI EN ISO 4674-1:2005	Warp ≥ 14 N / Weft ≥ 10 N
Seam resistance	UNI 10606	Warp 22 N / cm / Weft 9 N / cm
Ultimate elongation	UNI EN ISO 1421:2000	Warp ≥ 10 % / Weft ≥ 20 %
Peel adhesion	UNI EN ISO 2411:2000	Warp ≥ 40 N/5 cm / Weft ≥ 40 N / 5 cm
Dry abrasion strenght	UNI EN ISO 20344:2011	51.200 cycles Martindale
Wet abrasion strenght	UNI EN ISO 20344:2011	25.600 cycles Martindale
Flexing endurance	UNI 4818-13	≥ 100.000 cycles
Dry rub fastness	UNI EN ISO 105-X 12	5 Grey Scale
Wet rub fastness	UNI EN ISO 105-X 12	4,5 Grey Scale
Fastness to light	UNI EN ISO 105-B02	7 Grey Scale
Hidrolysis resistance	ISO 1419:1995 (E) C	> 5 Week
Fire reaction tests	BS 7176 Source 0-1 Cigarette test / Match test California Technical Bulletin 117:2013 Section E Part 1 EN 1021 1-2 IMO FTP 8 Res. A652 UNI 9175 1 EMME	